

Application No. 10/518,886  
Docket No. 2002B096/2  
Amdt. dated August 31, 2006  
Reply to OA of June 6, 2006 and  
Advisory OA dated August 15, 2006

**IN THE CLAIMS:**

Please cancel claim 8 and amend the claims as follows:

1. (Currently amended) A composition suitable for an air barrier comprising:  
an elastomer comprising C<sub>4</sub> to C<sub>7</sub> isoolefin derived units;  
a processing oil; and  
a plastomer, wherein the plastomer is a copolymer of ethylene derived units and C<sub>3</sub> to C<sub>10</sub> α-olefin derived units and has a density of less than 0.915 g/cm<sup>3</sup>,  
wherein the composition has a brittleness value of less than -41.0°C.
2. (Original) The composition of Claim 1, wherein the plastomer comprises ethylene derived units and from 10 wt% to 30 wt% of C<sub>3</sub> to C<sub>10</sub> α-olefin derived units.
3. (Original) The composition of Claim 1, wherein the plastomer comprises ethylene derived units and from 10 wt% to 30 wt% of units selected from 1-butene, 1-hexene and 1-octene derived units.
4. (Original) The composition of Claim 1, wherein the plastomer comprises ethylene derived units and from 10 wt% to 30 wt% of octene derived units.
5. (Previously presented) The composition of Claim 1, wherein the plastomer has a melt index of from 0.1 to 10 dg/min as measured by ASTM D 1238 at 190°C and 2.1 kg.
6. (Original) The composition of Claim 1, wherein the plastomer is present in the composition from 2 to 20 phr.
7. (Original) The composition of Claim 1, wherein the plastomer is present in the composition from 10 to 15 phr.

Application No. 10/518,886  
Docket No. 2002B096/2  
Amdt. dated August 31, 2006  
Reply to OA of June 6, 2006 and  
Advisory OA dated August 15, 2006

8. (Canceled)
9. (Previously presented) The composition of Claim 1, wherein the processing oil is selected from paraffinic oils, polybutene processing oils, and mixtures thereof.
10. (Previously presented) The composition of Claim 1, wherein the processing oil is present from 2 to 20 phr.
11. (Original) The composition of Claim 1, also comprising a filler selected from carbon black, modified carbon black, silicates, clay, exfoliated clay, and mixtures thereof.
12. (Previously presented) The composition of Claim 1, further comprising one or more components selected from natural rubbers, polyisoprene rubber, styrene-butadiene rubber (SBR), polybutadiene rubber, isoprene-butadiene rubber (IBR), styrene-isoprene-butadiene rubber (SIBR), ethylene-propylene rubber, ethylene-propylene-diene rubber (EPDM), polysulfide, nitrile rubber, propylene oxide polymers, poly(isobutylene-co-p-methylstyrene), halogenated poly(isobutylene-co-p-methylstyrene), poly(isobutylene-co-cyclopentadiene), halogenated poly(isobutylene-co-cyclopentadiene), and mixtures thereof.
13. (Previously presented) The composition of Claim 1, further comprising from 5 to 30 phr of one or more components selected from natural rubbers, polyisoprene rubber, styrene-butadiene rubber (SBR), polybutadiene rubber, isoprene-butadiene rubber (IBR), styrene-isoprene-butadiene rubber (SIBR), ethylene-propylene rubber, ethylene-propylene-diene rubber (EPDM), polysulfide, nitrile rubber, propylene oxide polymers, poly(isobutylene-co-p-methylstyrene), halogenated poly(isobutylene-co-p-methylstyrene), poly(isobutylene-co-cyclopentadiene), halogenated poly(isobutylene-co-cyclopentadiene), and mixtures thereof.
14. (Original) The composition of Claim 1, wherein the C<sub>4</sub> to C<sub>7</sub> isoolefin derived units are selected from isobutylene, isobutene, 2-methyl-1-butene, 3-methyl-1-butene, 2-methyl-2-butene, 1-butene, 2-butene, methyl vinyl ether, indene, vinyltrimethylsilane, hexene, and 4-methyl-1-pentene.

Application No. 10/518,886  
Docket No. 2002B096/2  
Amdt. dated August 31, 2006  
Reply to OA of June 6, 2006 and  
Advisory OA dated August 15, 2006

15. (Original) The composition of Claim 1, wherein the elastomer also comprises multiolefin derived units selected from isoprene, butadiene, 2,3-dimethyl-1,3-butadiene, myrcene, 6,6-dimethyl-fulvene, hexadiene, cyclopentadiene, and piperylene.
16. (Original) The composition of Claim 1, wherein the elastomer also comprises styrenic derived units selected from styrene, chlorostyrene, methoxystyrene, indene and indene derivatives,  $\alpha$ -methylstyrene, *o*-methylstyrene, *m*-methylstyrene, and *p*-methylstyrene, and *p*-tert-butylstyrene.
17. (Original) The composition of Claim 1, wherein the elastomer is halogenated.
18. (Original) The composition of Claim 1, also comprising a curative selected from sulfur, sulfur-based compounds, metal oxides, metal oxide complexes, fatty acids, peroxides, diamines, and mixtures thereof.
19. (Canceled)
20. (Previously presented) The composition of Claim 1, wherein the composition has a Shore A Hardness at 25°C of less than 55.
21. (Previously presented) The composition of Claim 1, wherein the composition has an air permeability at 65°C of less than  $3.50 \times 10^{-8} \text{ cm}^3\text{-cm/cm}^2\text{-sec-atm}$ .
22. (Previously presented) The composition of Claim 1, wherein the composition has an Adhesion to Carcass value of greater than 4 N/mm.
23. (Original) An article selected from tire curing bladders, innerliners, tire innertubes, and air sleeves made from the composition of Claim 1.

Application No. 10/518,886  
Docket No. 2002B096/2  
Amdt. dated August 31, 2006  
Reply to OA of June 6, 2006 and  
Advisory OA dated August 15, 2006

24. (Currently amended) A composition suitable for an air barrier comprising:  
polybutene processing oil;  
an elastomer comprising C<sub>4</sub> to C<sub>7</sub> isoolefin derived units; and  
a plastomer, wherein the plastomer is a copolymer of ethylene derived units and C<sub>3</sub> to C<sub>10</sub> α-olefin derived units and has a density of less than 0.915 g/cm<sup>3</sup>,  
wherein the composition has a brittleness value of less than -41.0°C.
25. (Original) The composition of Claim 24, wherein the plastomer comprises ethylene derived units and from 10 wt% to 30 wt% of C<sub>3</sub> to C<sub>10</sub> α-olefin derived units.
26. (Original) The composition of Claim 24, wherein the plastomer comprises ethylene derived units and from 10 wt% to 30 wt% of units selected from 1-butene, 1-hexene and 1-octene derived units.
27. (Original) The composition of Claim 24, wherein the plastomer comprises ethylene derived units and from 10 wt% to 30 wt% of octene derived units.
28. (Previously presented) The composition of Claim 24, wherein the plastomer has a melt index of from 0.1 to 10 dg/min as measured by ASTM D 1238 at 190°C and 2.1 kg.
29. (Original) The composition of Claim 24, wherein the plastomer is present in the composition from 2 to 20 phr.
30. (Original) The composition of Claim 24, wherein the plastomer is present in the composition from 3 to 10 phr.
31. (Original) The composition of Claim 24, wherein the polybutene processing oil has a number average molecular weight of from 900 to 8000.

Application No. 10/518,886  
Docket No. 2002B096/2  
Amdt. dated August 31, 2006  
Reply to OA of June 6, 2006 and  
Advisory OA dated August 15, 2006

32. (Original) The composition of Claim 24, wherein the polybutene processing oil is present from 2 to 20 phr.
33. (Original) The composition of Claim 24, also comprising a filler selected from carbon black, modified carbon black, silicates, clay, exfoliated clay, and mixtures thereof.
34. (Canceled)
35. (Previously presented) The composition of Claim 24, further comprising one or more components selected from natural rubbers, polyisoprene rubber, styrene-butadiene rubber (SBR), polybutadiene rubber, isoprene-butadiene rubber (IBR), styrene-isoprene-butadiene rubber (SIBR), ethylene-propylene rubber, ethylene-propylene-diene rubber (EPDM), polysulfide, nitrile rubber, propylene oxide polymers, poly(isobutylene-co-p-methylstyrene), halogenated poly(isobutylene-co-p-methylstyrene), poly(isobutylene-co-cyclopentadiene), halogenated poly(isobutylene-co-cyclopentadiene), and mixtures thereof.
36. (Previously presented) The composition of Claim 24, further comprising from 5 to 50 phr of one or more components selected from natural rubbers, polyisoprene rubber, styrene-butadiene rubber (SBR), polybutadiene rubber, isoprene-butadiene rubber (IBR), styrene-isoprene-butadiene rubber (SIBR), ethylene-propylene rubber, ethylene-propylene-diene rubber (EPDM), polysulfide, nitrile rubber, propylene oxide polymers, poly(isobutylene-co-p-methylstyrene), halogenated poly(isobutylene-co-p-methylstyrene), poly(isobutylene-co-cyclopentadiene), halogenated poly(isobutylene-co-cyclopentadiene), and mixtures thereof.
37. (Original) The composition of Claim 24, wherein the C<sub>4</sub> to C<sub>7</sub> isoolefin derived units are selected from isobutylene, isobutene, 2-methyl-1-butene, 3-methyl-1-butene, 2-methyl-2-butene, 1-butene, 2-butene, methyl vinyl ether, indene, vinyltrimethylsilane, hexene, and 4-methyl-1-pentene.

38. (Original) The composition of Claim 24, wherein the elastomer also comprises multiolefin derived units selected from isoprene, butadiene, 2,3-dimethyl-1,3-butadiene, myrcene, 6,6-dimethyl-fulvene, hexadiene, cyclopentadiene, and piperylene.
39. (Original) The composition of Claim 24, wherein the elastomer also comprises styrenic derived units selected from styrene, chlorostyrene, methoxystyrene, indene and indene derivatives,  $\alpha$ -methylstyrene, *o*-methylstyrene, *m*-methylstyrene, and *p*-methylstyrene, and *p*-tert-butylstyrene.
40. (Original) The composition of Claim 24, wherein the elastomer is halogenated.
41. (Original) The composition of Claim 24, also comprising a curative selected from sulfur, sulfur-based compounds, metal oxides, metal oxide complexes, fatty acids, peroxides, diamines, and mixtures thereof.
42. (Canceled)
43. (Previously presented) The composition of Claim 24, wherein the composition has a Shore A Hardness at 25°C of less than 50.
44. (Previously presented) The composition of Claim 24, wherein the composition has a aged Shore A Hardness at 25°C of less than 55.
45. (Previously presented) The composition of Claim 24, wherein the composition has an air permeability at 65°C of less than  $3.50 \times 10^{-8}$  cm<sup>3</sup>-cm/cm<sup>2</sup>-sec-atm.
46. (Previously presented) The composition of Claim 24, wherein the composition has an Adhesion to Carcass value of greater than 4 N/mm.
47. (Original) An article selected from tire curing bladders, innerliners, tire innertubes, and air sleeves made from the composition of Claim 24.

Application No. 10/518,886  
Docket No. 2002B096/2  
Amdt. dated August 31, 2006  
Reply to OA of June 6, 2006 and  
Advisory OA dated August 15, 2006

48. (Currently amended) A composition suitable for an air barrier comprising  
from 5 to 25 phr polybutene processing oil;  
halogenated star-branched butyl rubber;  
from 5 to 25 phr natural rubber; and  
from 5 to 25 phr of a plastomer, wherein the plastomer is a copolymer of ethylene  
derived units and C<sub>3</sub> to C<sub>10</sub>  $\alpha$ -olefin derived units and has a density of less than 0.915 g/cm<sup>3</sup>; and  
wherein the composition has a Brittleness value of less than  $\leq -41.0^{\circ}\text{C}$ .
49. (Original) The composition of Claim 48, wherein the polybutene processing oil has a  
number average molecular weight of from 900 to 3000.
50. (Original) An article selected from tire curing bladders, innerliners, tire innertubes, and air  
sleeves made from the composition of Claim 48.